



LAWRENCE
LIVERMORE
NATIONAL
LABORATORY

Materials at Extreme Compression

J. H. Eggert

June 12, 2014

LLNL, Board of Governors
Livermore, CA, United States
June 13, 2014 through June 13, 2014

Disclaimer

This document was prepared as an account of work sponsored by an agency of the United States government. Neither the United States government nor Lawrence Livermore National Security, LLC, nor any of their employees makes any warranty, expressed or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights. Reference herein to any specific commercial product, process, or service by trade name, trademark, manufacturer, or otherwise does not necessarily constitute or imply its endorsement, recommendation, or favoring by the United States government or Lawrence Livermore National Security, LLC. The views and opinions of authors expressed herein do not necessarily state or reflect those of the United States government or Lawrence Livermore National Security, LLC, and shall not be used for advertising or product endorsement purposes.

Materials at Extreme Compression

Jon Eggert

 Lawrence Livermore
National Laboratory

LLNL-PRES-XXXXXX

This work was performed under the auspices of the U.S. Department of Energy by Lawrence Livermore National Laboratory under Contract DE-AC52-07NA27344. Lawrence Livermore National Security, LLC



We have built a broad base of academic collaborators

- **Lawrence Livermore Laboratory**

- J.H. Eggert, D. Braun, J.R. Patterson, R.F. Smith, J.R. Rygg, J.A. Hawreliak, A. Lazicki, D. Fratanduono, **M. Beckwith^{^^}**, **F. Coppari^{^^}**, **R. Kraus^{^^}**, D. Hicks, Y. Ping, A. Fernandez, **M. Millot^{^^}**, D. Swift, P. Celliers, D.H. Kalantar, T. Perry, T. Arsenlis, G. Collins

- **Los Alamos Laboratory**

- C. Bolme

- **University of California, Berkeley**

- R. Jeanloz, **R.S. MacWilliams^{*}**, **D.K. Spaulding^{**}**

- **Princeton University**

- T. Duffy, **J. Wang[^]**, **June Wicks[^]**

- **University of Rochester**

- T. Boehly, B. Yaakobi

- **Stanford University**

- **A. Gleason^{^^}**, W. Mao

- **Commissariat a l'Energie Atomique, France**

- P. Loubeyre, S. Brygoo

- **University of Oxford, UK**

- J. Wark, A. Higginbotham, M. Suggit, **G. Mogni[^]**

- **National Research Council of Canada**

- D. Klug, Y. Yao

- **University of Edinburgh, Scotland**

- M. McMahon, **E. McBride[^]**, **R. Briggs^{^^}**

- **Additional Collaborators / Consultants**

- Andrew Comley, Brian Maddox, Hye-Sook Park, and Bruce Remington

- **Plus farget fabrication, Omega and NIF facility and diagnostic teams.**


[^]Student

^{^^}Post-Doc


^{*}Currently, University of Edinburgh

^{**}Currently, Harvard University

Matter at High Energy Density (HED) is found throughout our universe




Just a few years ago, ultra-high pressure phase diagrams were considered to be very simple



**Physics
Gets
Simple!**


Above 200 GPa Sodium becomes a large band-gap insulator! -- Electride --




“... what the present results most assuredly demonstrate is the importance of pressure in revealing the limitations of previously hallowed models of solids”

—Neil Ashcroft (Nature, 2009).


FCC, 65 GPa




cl16, 108 GPa




oP8, 119 GPa



tl19, 147 GPa
Incommensurate




hP4, 190 GPa
Insulating, Transparent
Electride



Increasing Structural Complexity

Traditional view that *all* materials become simple at high pressure is incorrect!

Many materials are predicted to adopt complex structures in high pressure solid and fluid phases



Canales, PRL, (2012)
Hamel et al, 2014

Using laser-driven compression and the NIF we are study Extreme-Compression ($\rho/\rho_0 > 2$) Science

We want to measure:

Stress-Density



Temperature

Structure

Solid-Solid Phase Transitions




Solid-Liquid Phase Transitions

We use a shaped laser pulse to control the time-dependent laser ablation drive pressure



Steady Shocks -> Impedance Matching
 Decaying Shocks -> U_s vs R , T , Heat Capacity
 Ramp Compression -> Lower Temperature


Ramp-compression EOS of nano-crystalline diamond to 50 Mbar.



Smith, et. al, *Nature*, accepted for publication.


Resolving x-ray absorption structure gives temperature along different compression paths

EXAFS data collected in 50 ps snapshot



Y. Ping, et al., PRL, **111**,
(2013).

T versus P data for Fe shows structure is HCP and information on Earth's core conditions



**Using the laser-driven compression and the NIF
we will study Extreme Compression Science**

We want to measure:

Stress-Density



Temperature

Structure

Solid-Solid Phase Transitions


Solid-Liquid Phase Transitions

Using LDRD funding, we developed in-situ x-ray diffraction at Janus and Omega




Demonstrated at Omega, PXRDIP
(Powder X-Ray Diffraction Image Plates)

In situ diffraction provides conclusive crystal structure. Demonstrated at Omega





Rygg, et al., RSI, **83**, 113904 (2012)




De-warped image plate data

We have observed Shock-Melt – Refreeze for first time ever in Sn at Omega


[May 28, 2014]



Shot 18450
Long Delay
=> All Liquid





Shot 18452
Reduced Delay
=> Liquid + Refreeze





Rick Kraus, Federica Coppari

We are fielding diffraction on NIF (13 shots so far) TARDIS (TARget Diffraction In Situ) diagnostic



**Three image plates collect
the diffraction data**



Last week we observed at least 9 diffraction lines from Pb at ~2.5 Mbar, and the (undriven) Ta pinhole



HIGH-PRESSURE PHASE TRANSITION AND EQUATION OF STATE OF LEAD TO 238 GPa

H.K. Mao*, Y. Wu**, J.F. Shu*, J.Z. Hu*, R.J. Hemley* and D.E. Cox†

Our observation of BCC phase suggests that we can study equilibrium solid phase diagrams on the NIF



Our expanding reach in extreme-compression physics

We can ramp compress solids to 1-5 TPa and measure absolute stress-density EOS

We see direct evidence for phase transitions, melt, and refreeze in materials